

**Kiwa GmbH**  
TBU  
Gutenbergstraße 29  
48268 Greven

Tel. +49 (0)2571 9872 0  
Fax +49 (0)2571 9872 99  
infokiwagreven@kiwa.de  
www.kiwa.de

## Test Report Nr. 2.1/13821/1460.0.1-2015e

### General

Issued: 03.08.2016

Order by: **Dural GmbH**  
**Südring 11**  
**56412 Ruppach-Goldhausen**  
**Germany**

Objekt/Material: Decapling- and sealingmat (yellow) made of polypropylen with an grid (topside)  
and an nonwoven on the bottom (white) made of polypropylen.

**Durabase CI++**  
(declaration by customer)

Order date: 15.12.2015

Samples delivered: 02.06.2016

Tests:	Standard	Issue
1. Determination of watertightness	DIN EN 1928	07.2000

The results apply exclusively to the specimens submitted.  
The date of testing is reported on the enclosed enclosure/-es.  
Results are reported to the accuracy given in the standards. In statistical evaluation, the measured accuracy is taken.

**This test report contains 2 pages.**  
**It may not be published in parts.**




## 1. Determination of watertightness

Samples: 3 Samples (Ø 135 mm) of DURABASE CI++  
 Date of test: 27.07.2016, 28.07.2016, 02.08.2016  
 Test pressure: 1,5 bar for 24 h  
 Test procedure: The Determination of watertightness was tested according to DIN EN 1928 (Procedure B).  
 The Samples were sealed with an 2K S50 adhesive on the sample edge and mounted with the nonwoven side to the water  
 The test is passed if all 3 samples are watertight after 24 h.

**Result:** All 3 samples were watertight after 24 h with the test pressure of 1,5 bar.

*i.v.d. Stauber*  
 i. V. Dipl.-Ing. (FH) Christoph Staubermann  
 (Head of test laboratory)



*i.A. Kriz*  
 i. A. Alexander Kriz, B.Sc.  
 (Staff of laboratory)